

ABSTRACT

5 A peroxide-crosslinked rubber composition having a
superior anti-blooming property of a crosslinking agent
and a high hardness containing (A) more than 60 parts by
weight but not more than 95 parts by weight of rubber
selected from NR, IR, SBR, BR, EPM, EPDM, silicone rubber
and/or fluororubber and (B) 5 parts by weight but less
than 40 parts by weight of a polar polymer having a
10 solubility parameter (Sp value) of at least 17.6 ($\text{Pa}^{1/2}$)
and a weight average molecular weight of at least
100,000.